

Technical Data Sheet

Benzoflex™ 352 Plasticizer

Applications

- Adhesives/sealants-b&c
- General industrial coatings
- Paints & coatings

Product Description

Benzoflex™ 352 is a white flake solid with a melt point of 118°C which can offer significant performance advantages in a variety of hot melt adhesive applications. It also modifies melt flow characteristics with improved resistance to yellowing in powder coatings.

Typical Properties

Property	Typical Value, Units
General	
Acidity (wt%)	0.2 max.
Color Pt-Co	30 max.
Refractive Index @ 25°C	Solid
Specific Gravity @ 20°C/20°C	1.136
Boiling Point	Solid
Flash Point Setaflash Closed Cup	450 °F (232 °C)
Freezing Point	244 °F (118 °C)
Vapor Pressure @ 20°C	Solid
Viscosity @ 25°C	Solid
Wt/Vol @ 20°C	9.51 lb/gal (1.14 kg/L)

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

© 2023 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.